

Dikte van de coating

Corrosieklasse volgens ISO 12944-2

	Coating metaal					
	Zinc - Zn99.99			Zinc-Aluminium - ZnAl15		
	as	as + s	as + s + oc	as	as + s	as + s + oc
C1 Zeer laag	80	80	50	80	80	50
C2 Laag	150	80	50	150	80	50
C3 Medium	150	100	80	150	100	80
C4 Hoog	NR	150	100*	200	150	80
C5 Zeer hoog	NR	NR	100*	200	150	80
CX Extreem	NR	NR	NR	250	150	100*
Im1	80	80	50	80	80	50
Im2	150	80	50	150	80	50
Im3	80	80	50	80	80	50
Im4	150	80	50	150	80	50

as as sprayed

s sealed

oc organic coating

NR not recommended

* Een organische coating aangepast aan de omgeving vormt een essentieel deel van het coatingsysteem